

TEST REPORT OF GGBFS

Sr No	Parametrs	Unit	Result Obtained	Protocol
1	Loss on Ignition	%	1.6	EN 196-2:1987
2	Insoluable Residue	%	0.85	EN 196-2:1987
3	Magnesia(Mgo)	%	6.52	EN 196-2:1987
4	Sulphate Content as Sulphite	%	0.15	EN 196-2:1987
5	Chloride(Cl)	%	0.0102	EN 196-2:1987
6	Insoluable Residue	%	92	EN 196-2:1987
7	Magnese Oxide	%	0.039	EN 196-2:1987
8	(Cao+Mgo)/Sio2	%	1.22	EN 196-2:1987
9	Chemical Modulus (Cao/SiO2)	%	0.96	EN 196-2:1987
10	Finesss by air permelability	%	380	IS 4031-Part 2
11	Iron oxide as Fe2O3	%	1.83	BS 6699-1992
12	Sodium Chloride	%	0.655	IS 4032-1985
13	Free Lime as Cao	%	0.77	IS 4032-1985